



Zytel® 101L BKB009

NYLON RESIN

Zytel® 尼龙树脂的共性包括良好的机械和物理性能，例如高机械强度，刚性和韧性之间良好的平衡，良好的高温性能、电性能和阻燃性能，优异的耐磨损和耐化学品性能。另外，Zytel®

尼龙树脂有不同改性和增强规格为特殊加工和终端客户提供定制的性能。Zytel®

尼龙树脂，包括大多数阻燃规格，提供了染色可能性。

Zytel® 尼龙树脂良好的热稳定性通常使正确处理的生产废弃物回收成为可能。如果不能回收使用，杜邦建议的优先选择是在合适的装置中焚烧进行能量回收（基体树脂-31kJ/g）。废弃处理需遵守当地法规。

Zytel® 尼龙树脂通常应用于要求严苛的汽车、家具、家用电器、运动器材和建筑业。

Zytel® 101L BKB009是一种未增强 尼龙66

总说明

树脂鉴别	PA66	ISO 1043
制品标识码	>PA66<	ISO 11469
ISO名称	ISO 16396-PA66,,M1CG1R,S14-030	

机械性能

	dry/cond.		
拉伸模量	3050/1400 ^[DS]	MPa	ISO 527-1/-2
屈服应力	88/50 ^[DS]	MPa	ISO 527-1/-2
屈服伸长率	4.6/25 ^[DS]	%	ISO 527-1/-2
名义断裂伸长率	16/>50	%	ISO 527-1/-2
弯曲模量	2800/1200 ^[DS]	MPa	ISO 178
简支梁无缺口冲击强度, +23°C	203/-	kJ/m ²	ISO 179/1eU
简支梁无缺口冲击强度, -30°C	134/-	kJ/m ²	ISO 179/1eU
简支梁缺口冲击强度, +23°C	4/-	kJ/m ²	ISO 179/1eA
简支梁缺口冲击强度, -30°C	3.7/-	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.37/0.43	-	

[DS]: Derived from similar grade

热性能

	dry/cond.		
熔融温度, 10°C/min	262/*	°C	ISO 11357-1/-3
玻璃化转变温度, 10°C/min	65/-	°C	ISO 11357-1/-2
热变形温度, 1.80 MPa	70/*	°C	ISO 75-1/-2
热变形温度, 0.45 MPa	190/*	°C	ISO 75-1/-2
相对温度指数, 电气性能, 0.75mm	130	°C	UL 746B
相对温度指数, 电气性能, 1.5mm	130	°C	UL 746B
相对温度指数, 电气性能, 3mm	130	°C	UL 746B
相对温度指数, 电气性能, 6mm	130	°C	UL 746B
相对温度指数, 冲击, 0.75mm	75	°C	UL 746B
相对温度指数, 冲击, 1.5mm	75	°C	UL 746B
相对温度指数, 冲击, 3mm	75	°C	UL 746B
相对温度指数, 冲击, 6mm	75	°C	UL 746B



Zytel® 101L BKB009

NYLON RESIN

相对温度指数, 强度, 0.75mm	85	°C	UL 746B
相对温度指数, 强度, 1.5mm	85/*	°C	UL 746B
相对温度指数, 强度, 3mm	85	°C	UL 746B
相对温度指数, 强度, 6mm	85	°C	UL 746B

燃烧性能

	dry/cond.		
1.5mm名义厚度时的燃烧性	V-2/*	class	IEC 60695-11-10
测试用试样的厚度	1.5/*	mm	IEC 60695-11-10
UL注册	yes/*	-	UL 94
厚度为h时的燃烧性	V-2/*	class	IEC 60695-11-10
测试用试样的厚度	0.71/*	mm	IEC 60695-11-10
UL注册	yes/* ^[1]	-	UL 94
灼热丝燃烧指数, 0.75mm	960/-	°C	IEC 60695-2-12
灼热丝燃烧指数, 1.5mm	960/-	°C	IEC 60695-2-12
灼热丝燃烧指数, 3mm	960/-	°C	IEC 60695-2-12
灼热丝起燃温度, 0.75mm	725/-	°C	IEC 60695-2-13
灼热丝起燃温度, 1.5mm	750/-	°C	IEC 60695-2-13
灼热丝起燃温度, 3mm	800/-	°C	IEC 60695-2-13
FMVSS Class	B	-	ISO 3795 (FMVSS 302)
燃烧速率, 厚度: 1毫米	<80	mm/min	ISO 3795 (FMVSS 302)
[1]: UL yellow card (f1)			

其它性能

	dry/cond.		
密度	1140/-	kg/m ³	ISO 1183

VDA性能

	dry/cond.		
有机化合物的排放	5	□ gC/g	VDA 277
气味测试	3	class	VDA 270
雾化	99/*	%	ISO 6452
雾化	0.1/*	mg	ISO 6452

注塑

建议干燥	是
干燥温度	80 °C
干燥时间, 除湿干燥机	2 - 4 h
加工前水分含量	≤ 0.2 %
最优熔体温度	290 °C
注塑 熔体温度	280 °C
注塑 熔体温度	300 °C
螺杆最大切线速度	0.4 m/s
最优模具温度	70 °C
模具温度	50 °C
模具温度	90 °C

Zytel® 101L BKB009

NYLON RESIN

保压范围
保压时间
喷射温度

50 - 100 MPa
4 s/mm
190 °C

耐化学性

酸类

- ✓ 醋酸 (5g/100g), 23°C
- ✓ 柠檬酸溶液 (10g/100g), 23°C
- ✓ 乳酸 (10g/100g), 23°C
- ✗ 盐酸 (36g/100g), 23°C
- ✗ 硝酸 (40g/100g), 23°C
- ✗ 硫酸 (38g/100g), 23°C
- ✗ 硫酸 (5g/100g), 23°C
- ✗ 铬酸溶液 (40g/100g), 23°C

碱类

- ✗ 氢氧化钠溶液 (35g/100g), 23°C
- ✓ 氢氧化钠溶液 (1g/100g), 23°C
- ✓ 氨水(氢氧化铵) (10g/100g), 23°C

醇类

- ✓ 异丙醇, 23°C
- ✓ 甲醇, 23°C
- ✓ 乙醇, 23°C

碳氢化合物

- ✓ n-乙烷, 23°C
- ✓ 甲苯, 23°C
- ✓ 异辛烷, 23°C

酮类

- ✓ 丙酮, 23°C

醚类

- ✓ (二)乙醚, 23°C

矿物油

- ✓ SAE 10W40号多效润滑油, 23°C
- ✗ SAE 10W40号多效润滑油, 130°C
- ✗ SAE 89/90号变速箱润滑油, 130°C
- ✓ 绝缘油, 23°C

标准燃油

- ✓ ISO 1817 燃油1号, 60°C
- ✓ ISO 1817 燃油2号, 60°C
- ✓ ISO 1817 燃油3号, 60°C
- ✓ ISO 1817 燃油4号, 60°C
- ✓ 不含酒精的标准燃油(优先使用C类ISO 1817 燃油), 23°C
- ✓ 含酒精的标准燃油(优先使用4号ISO 1817 燃油), 23°C

Zytel® 101L BKB009

NYLON RESIN

- ✓ 柴油(优先使用F类ISO 1817液体), 23°C
- ✗ 柴油(优先使用F类ISO 1817液体), 90°C
- ✗ 柴油(优先使用F类ISO 1817液体), >90°C

盐溶液

- ✓ 氯化钠溶液(10g/100g), 23°C
- ✗ 次氯化钠溶液 (10g/100g), 23°C
- ✓ 碳酸钠溶液 (20g/100g), 23°C
- ✓ 碳酸钠溶液 (2g/100g), 23°C
- ✗ 氯化锌溶液 (50g/100g), 23°C

其它

- ✓ 乙酸乙酯, 23°C
- ✗ 过氧化氢, 23°C
- ✗ DOT4号刹车油, 130°C
- ✗ 乙二醇水溶液 (50g/100g), 108°C
- ✓ 1g/100g 基苯氧- 聚环氧乙烷乙烯水溶液, 23°C
- ✓ 油酸 (50g/100g) + 橄榄油 (50g/100g), 23°C
- ✓ 水, 23°C
- ✗ 去离子水, 90°C
- ✗ 酚溶液(5g/100g), 23°C

Symbols used:

- ✓ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
- ✗ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.