



Rynite® FR531 NC010

THERMOPLASTIC POLYESTER RESIN

Rynite® 热塑性聚酯的共性包括良好的机械和物理性能，例如强度和刚性之间良好的平衡、尺寸稳定性、耐蠕变、耐热老化、高表面光泽和固有地高温下良好的电气性能。可在很宽泛的温度范围内加工，有很好的流动性能。

Rynite® 热塑性聚酯通常应用于要求严苛的汽车、电子电器工业，成功取代金属、热固性材料和其他热塑性聚合物。

Rynite® FR531 NC010是一种45% 增强, 阻燃, PET

总说明

树脂鉴别	PET-(GF+MD)38FR(17)	ISO 1043
制品标识码	>PET-(GF+MD)38FR(17)<	ISO 11469

流变性能

模塑收缩率, 平行	0.1 %	ISO 294-4, 2577
模塑收缩率, 垂直	0.7 %	ISO 294-4, 2577
模塑收缩率	0.2 %	ISO 294-4
模塑收缩率	0.1 %	ISO 294-4

机械性能

拉伸模量	12600 MPa	ISO 527-1/-2
断裂应力	129 MPa	ISO 527-1/-2
断裂伸长率	1.6 %	ISO 527-1/-2
简支梁无缺口冲击强度, +23°C	36 kJ/m ²	ISO 179/1eU
简支梁缺口冲击强度, +23°C	10 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.33 -	

热性能

熔融温度, 10°C/min	247 °C	ISO 11357-1/-3
玻璃化转变温度, 10°C/min	90 °C	ISO 11357-1/-2
热变形温度, 1.80 MPa	218 °C	ISO 75-1/-2
相对温度指数, 电气性能, 0.75mm	155 °C	UL 746B
相对温度指数, 电气性能, 1.5mm	155 °C	UL 746B
相对温度指数, 电气性能, 3mm	155 °C	UL 746B
相对温度指数, 冲击, 0.75mm	155 °C	UL 746B
相对温度指数, 冲击, 1.5mm	155 °C	UL 746B
相对温度指数, 冲击, 3mm	155 °C	UL 746B
相对温度指数, 强度, 0.75mm	155 °C	UL 746B
相对温度指数, 强度, 1.5mm	155 °C	UL 746B
相对温度指数, 强度, 3mm	155 °C	UL 746B



Rynite® FR531 NC010

THERMOPLASTIC POLYESTER RESIN

燃烧性能

1.5mm名义厚度时的燃烧性	V-0 class	IEC 60695-11-10
测试用试样的厚度	1.5 mm	IEC 60695-11-10
UL注册	yes -	UL 94
厚度为h时的燃烧性	V-0 class	IEC 60695-11-10
测试用试样的厚度	0.75 mm	IEC 60695-11-10
UL注册	yes -	UL 94
厚度为h时的5V燃烧性	5VA class	IEC 60695-11-20
测试用试样的厚度	2 mm	IEC 60695-11-20
UL注册	yes -	UL 94
灼热丝燃烧指数, 0.75mm	960 °C	IEC 60695-2-12
灼热丝燃烧指数, 1.5mm	960 °C	IEC 60695-2-12
灼热丝燃烧指数, 2mm	960 °C	IEC 60695-2-12
灼热丝燃烧指数, 3mm	960 °C	IEC 60695-2-12
灼热丝起燃温度, 0.75mm	900 °C	IEC 60695-2-13
灼热丝起燃温度, 1.5mm	900 °C	IEC 60695-2-13
灼热丝起燃温度, 2mm	900 °C	IEC 60695-2-13
灼热丝起燃温度, 3mm	875 °C	IEC 60695-2-13
灼热丝温度, 无火, 1mm	850 °C	IEC 60335-1
灼热丝温度, 无火, 2mm	800 °C	IEC 60335-1
FMVSS Class	DNI -	ISO 3795 (FMVSS 302)

电性能

相对介电常数., 100Hz	4.6 -	IEC 62631-2-1
相对介电常数., 1MHz	4.3 -	IEC 62631-2-1
介质损耗因子, 100Hz	43.7 E-4	IEC 62631-2-1
介质损耗因子, 1MHz	135 E-4	IEC 62631-2-1
体积电阻率	>1E13 Ohm.m	IEC 62631-3-1
表面电阻率	1E13 Ohm	IEC 62631-3-2
介电强度	34 kV/mm	IEC 60243-1
相对漏电起痕指数	325 -	IEC 60112
相对漏电起痕指数	2 PLC	UL 746A

其它性能

密度	1830 kg/m ³	ISO 1183
----	------------------------	----------

注塑

建议干燥	是
干燥温度	120 °C
干燥时间, 除湿干燥机	4 - 6 h
加工前水分含量	≤ 0.02 ^[1] %
优良熔体温度	280 °C
注塑 熔体温度	270 °C



Rynite® FR531 NC010

THERMOPLASTIC POLYESTER RESIN

注塑 熔体温度	290 °C
螺杆大的切线速度	0.2 m/s
优良模具温度	110 °C
模具温度	100 °C
模具温度	120 ^[2] °C
保压范围	≥ 80 MPa
保压时间	4 s/mm
背压	As low as possible MPa
喷射温度	170 °C

[1]: At levels above 0.02%, strength and toughness will decrease, even though parts may not exhibit surface defects.

[2]: (6mm - 1mm thickness)

典型数据

添加剂

阻燃剂

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.