



组件 - 塑料
UL 档案号: E45034

POLYPLASTICS CO LTD
18-1 KONAN
2-CHOME
MINATO-KU, TOKYO 108-8280 Japan



Duracon: TR-10D
Acetal Polyoxymethylene (POM), pellets

可燃性	值	测试方法
UL 阻燃等级		
0.75 mm, ALL	HB	UL 94
1.5 mm, ALL	HB	UL 94
3.0 mm, ALL	HB	UL 94
3.0 mm, ALL	HB40	IEC 60695-11-10, -20
0.75 mm, ALL	HB75	IEC 60695-11-10, -20
1.5 mm, ALL	HB75	IEC 60695-11-10, -20
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746A
0.75 mm	PLC 4	
1.5 mm	PLC 4	
3.0 mm	PLC 3	
高电弧燃烧指数(HAI)		UL 746A
0.75 mm	PLC 0	
1.5 mm	PLC 0	
3.0 mm	PLC 0	
相比耐漏电起痕指数(CTI)	PLC 0	UL 746A
介电强度	35 kV/mm	ASTM D149
高电压电弧起痕速率 (HVTR)	PLC 0	UL 746A
体积电阻率	1.0E+14 ohms·cm	ASTM D257 IEC 60093
耐电弧性	PLC 5	ASTM D495
物理性能	值	测试方法
Dimensional Change	0.0 %	ASTM D1042 ISO 2796