



POLYPLASTICS CO LTD
18-1 KONAN
2-CHOME
MINATO-KU, TOKYO 108-8280 Japan



Duracon: TR-20(r7)

Acetal Polyoxymethylene (POM), pellets

(r7) - Virgin and Re grind from 1 to 50% by weight inclusive have the same basic material characteristics for thicknesses of 1.5mm and above, except for the RTI's are 50C for all three properties for Re grind from 26 - 50%.

可燃性	值	测试方法
UL 阻燃等级		
0.75 mm, ALL	HB	UL 94
1.5 mm, ALL	HB	UL 94
0.75 mm, ALL	HB75	IEC 60695-11-10, -20
1.5 mm, ALL	HB75	IEC 60695-11-10, -20
热性能	值	测试方法
RTI Elec		UL 746B
0.75 mm	110 °C	
1.5 mm	110 °C	
RTI Imp		UL 746B
0.75 mm	95.0 °C	
1.5 mm	100 °C	
RTI		UL 746B
0.75 mm	95.0 °C	
1.5 mm	100 °C	