



POLYPLASTICS CO LTD
18-1 KONAN 2-CHOME
MINATO-KU, TOKYO 108-8280 Japan



Duranex: 7390W(n)

Polybutylene Terephthalate (PBT), pellets

(n) - May be followed by a letter D, H, L or R to denote melt flow.

可燃性	值	测试方法
UL 阻燃等级		UL 94
0.75 mm, ALL	V-0	IEC 60695-11-10, -20
1.5 mm, ALL	V-0	
3.0 mm, ALL	V-0	
2.0 mm, BK	5VA	
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746A
0.75 mm	PLC 4	
1.5 mm	PLC 3	
2.0 mm	PLC 3	
3.0 mm	PLC 2	
高电弧燃烧指数(HAI)		UL 746A
0.75 mm	PLC 1	
1.5 mm	PLC 1	
2.0 mm	PLC 1	
3.0 mm	PLC 1	
相比耐漏电起痕指数(CTI)	PLC 2	UL 746A
介电强度	27 kV/mm	ASTM D149
高电压电弧起痕速率 (HVTR)	PLC 4	UL 746A
体积电阻率	1.0E+14 ohms-cm	ASTM D257 IEC 60093
耐电弧性	PLC 6	ASTM D495
热性能	值	测试方法
RTI Elec		UL 746B
0.75 mm	140 °C	
1.5 mm	140 °C	
2.0 mm	140 °C	
3.0 mm	140 °C	
RTI Imp		UL 746B
0.75 mm	130 °C	
1.5 mm	130 °C	
2.0 mm	130 °C	
3.0 mm	130 °C	
RTI		UL 746B
0.75 mm	140 °C	
1.5 mm	140 °C	
2.0 mm	140 °C	
3.0 mm	140 °C	

组件 - 塑料

UL 档案号: E213445



物理性能	值	测试方法
Dimensional Change	0.0 %	ASTM D1042 ISO 2796