

# Ultramid® A3WG8 BK20560

## Polyamide 66



### Product Description

Ultramid A3WG8 BK20560 is a 40% glass fiber reinforced, pigmented black PA66. This grade offers excellent heat resistance and high strength. It is designed for industrial applications requiring excellent strength and stiffness.

### Applications

Typical applications include gear wheels, solenoid valve housings, cable attachments, automotive fuel distributors, pedals and components for automotive gear shifts.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm <sup>3</sup>	1183	1.46	
Moisture, % (50% RH)	62	1.5	
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa 23C	527	13,200	-
Tensile stress at break, MPa 23C	527	220	-
Tensile strain at break, % 23C	527	3.0	-
Flexural Modulus, MPa 23C	178	12,000	-
IMPACT	ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m <sup>2</sup> -40C 23C	180	12 14	- -
Charpy Notched, kJ/m <sup>2</sup> -30C 23C	179	11 13	- -
Charpy Unnotched, kJ/m <sup>2</sup> -30C 23C	179	83 95	- -
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, C	3146	260	-
HDT A, C	75	250	-
HDT B, C	75	260	-

### Processing Guidelines

**Material Handling**  
Max. Water content: 0.15%

Product is supplied in sealed containers and drying prior to molding is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80C (176F) is recommended. Drying time is dependent on moisture level, However 2-4 hours is generally sufficient. Recommended moisture levels for achieving optimum surface qualities and mechanical properties is 0.05% - 0.12%. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet. Alternatively, please contact your BASF representative.

**Typical Profile**

Melt Temperature 280-305C (536-581F)

Mold Temperature 80-90C (176-194F)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

**Mold Temperatures**

A mold temperature of 80-90C (176-194F) is recommended, however temperatures of as low as 45C (113F) and as high as 105C (221F) can be used where applicable.

**Pressures**

Injection pressure controls the filling of the part and should be applied for 90% of ram travel.

Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage.

**Fill Rate**

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

**Note**

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.