

Ultradur® B 4300 G3 LS High Speed BK15045

Polybutylene Terephthalate (PBT)



Product Description

Ultradur B 4300 G3 LS High Speed BK15045 is a high flow, fast cycling with low warpage, 15% glass filled, pigmented black, injection molding PBT for industrial parts, rigid tough and dimensional stable applications. This grade is suitable for laser marking.

| PHYSICAL | ISO Test Method | Property Value |
|--|-----------------|----------------|
| Density, g/cm ³ | 1183 | 1.41 |
| Moisture, % | 62 | |
| (50% RH) | | 0.2 |
| (Saturation) | | 0.4 |
| MECHANICAL | ISO Test Method | Property Value |
| Tensile Modulus, MPa | 527 | |
| 23C | | 5,500 |
| Tensile stress at break, MPa | 527 | |
| 23C | | 99 |
| Tensile strain at break, % | 527 | |
| 23C | | 3.6 |
| Flexural Modulus, MPa | 178 | |
| 23C | | 5,200 |
| IMPACT | ISO Test Method | Property Value |
| Izod Notched Impact, kJ/m ² | 180 | |
| 23C | | 4.6 |
| Charpy Notched, kJ/m ² | 179 | |
| 23C | | 4.7 |
| Charpy Unnotched, kJ/m ² | 179 | |
| 23C | | 27 |
| THERMAL | ISO Test Method | Property Value |
| Melting Point, C | 3146 | 223 |
| HDT A, C | 75 | 189 |

Processing Guidelines

Material Handling

Max. Water content: 0.04%

To ensure optimum part performance, this product must be dried prior to molding and maintained at a moisture level of less than 0.04%. Dehumidifying or desiccant dryers operating at 100-120C (212-248F) for 4 hours drying time are recommended. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet. Alternatively, please contact your BASF representative.

Typical Profile

Melt Temperature 250-270C (482-518F)

Mold Temperature 60-100C (140-212F)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

Mold Temperatures

This product can be processed over mold temperatures of 60-100C (140-212F); however, for optimizing surface appearance, dimensional stability and part performance, mold surface temperatures of at least 80C (176F) are preferred.

Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. A maximum of 10 bar (145 psi) is recommended due to the risk of excessive shear.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.